

5

<p>92-054171/07 L02 SHIK- 17.04.90 SHIKOKU SOGO KENKYU (TAKJ) 17.04.90-JP-102233 (07.01.92) C04b-14/02 C04b-18/08 C04b-20 C04b-22/06 C04b-24 C04b-28/04 Cement compsn. for water-tight concrete - has amorphous silica fines contg. discharged fly ash of specified size which is then kneaded with aggregate and water C92-024645</p>	<p>1(2-D13, 2-D14G)</p>
<p>Full Patentees: Shikoku Sogo Kenkyu; Taisei Construction KK Compsn is made by adding a suitable amt. of water reducing agent, fly ash and amorphous silica fines in which the fly ash discharged on firing coal is up to 20 microns in size. Resulting fly ash is then kneaded with aggregate and water. USE - Used for water-tight concrete for use at the underground parts. 16pp Dwg.No.0/4)</p>	

BEST AVAILABLE COPY